



CP 1800

Clearcoat 2K HS 2:1

Rocket Clear stands as an ideal solution for repairing various items with small to medium-sized surfaces. Noteworthy for its excellent flow ability and rapid drying and evaporation times, Rocket Clear offers unparalleled efficiency. **CP 1800**, uniquely merges the benefits of fast and slow clearcoats, ensuring a high final hardness, making it particularly well-suited for "smart repairs."

For added convenience, **Rocket Clear** is available in 1 and 5-Litre tins, providing a practical and versatile choice for a range of repair projects.

PACKAGING	
Volume	Collective packaging
1 l + 0.5 l (hardener)	6 pcs. + 6 pcs.
5 l + 2.5 l (hardener)	4 pcs. + 4 pcs.



SCRATCH-
RESISTANT



VERY SHORT
DRYING TIME



PERFECT FOR
SMART REPAIR



GIVES A HIGH GLOSS
AND INTENSITY



GOOD PAINT FLOW



SPRAY VISCOSITY

16-18 sec. DIN Flow Cup 4 mm



RECOMMENDED SIZES FOR PAINT STRAINER

125-190 µm



PAINT EFFICIENCY

~7-8 m²/l



POT LIFE

~2-3 hrs



DRY FILM THICKNESS

1 coat - ~25 µm



POLISHING

Abrade with **P1500-P2500** range. The polishing can then be carried out with the **Profix polishing system**



MINIMUM SHELF LIFE

CP 1800: 24 months in originally sealed packaging
CP 269: 12 months in originally sealed packaging



VOC

2004/42/WE/IIIB(e)(840) 535

PROCESS

PROGRESS

PROGRESS



SUBSTRATE PREPARATION

Ensure basecoat surface is clean using antistatic cloth before applying clearcoat for a flawless finish



MIXING RATIO

2:1
100 parts of **CP 1800**
50 parts of hardener **CP 269**
add **10-20%** of thinner **CP 040/ CP 070/ CP 055/ CP 075**



SPRAY GUN SETTINGS

Nozzle size: **1.2-1.4 mm**;
Operating pressure: HVLP/RP **1.8-2.0 bar**



APPLICATION

2 full coats



EVAPORATION TIME AFTER APPLICATION

3-5 min after application at **20°C**
and **65%** relative humidity



DRYING

Drying times at **20°C** and **65%** relative humidity:
- dust dryness: **30 min**
- non-tacking: **1 hrs**
- thoroughly: **~1,5- 2 hrs**

Drying times at **40°C** and **65%** relative humidity:
- for assembly: **30 min**

Drying times at **60°C** and **65%** relative humidity:
- for assembly: **15 min**



IR DRYING

~20 min